



FLOORFIX TILE ADHESIVE



DUNLOP FLOORFIX is an economical, cement-based floor tile adhesive for the fixing of ceramic tiles in indoor and covered outdoor situations. It can be used over concrete floors or sand and cement screeded floors. The adhesive is recommended for fixing ceramic, quarry tiles, slate and natural stone e.g., sandstone. Where movement is anticipated, use DUNLOP FLOOR TILE ADHESIVE or use in conjunction with DUNLOP PRIMER AND ADDITIVE.

SURFACE PREPARATION

The surface must be clean, true and free from dust, oil, laitance etc.

Concrete

Concrete floors must be at least 4 weeks old. Steel trowelled surfaces must be roughened mechanically prior to tiling. A wood float finish is the recommended surface for tiling using DUNLOP FLOORFIX.

Sand Cement Screed:

The screed is to consist of one part cement to three or four parts sand. Leave the screed with a wood float finish to establish a mechanical key. Allow screed at least 7 days to cure prior to tiling. It should be approximately 15mm in thickness for fully bonded screed and 40mm minimum for self supporting screed.

MIXING

The mixed material is usable for up to 2 hours.

1. Use approximately 3.5L of water with 15kg of the powder.
2. Add powder to clean water in a suitable container and mix to a thick creamy consistency.
3. Allow to stand for 5 minutes, re-stir the mixture thoroughly and it is ready for use. Do not add additional water.

APPLICATION

1. Apply the DUNLOP FLOORFIX to the surface with a 10 x 10 x 10mm notched trowel to achieve 100% coverage on the back of the tile.
2. Spread only 1 square metre at a time and ensure a skin has not developed on the adhesive before bedding the tiles.
3. Press and slide the tile into position ensuring the whole of the back of the tile is in good contact with the adhesive. Deeply keyed quarry tiles and some extruded tiles may require buttering of the adhesive on the back of the tiles to ensure 100% coverage.
4. The final adhesive bed must not be less than 3mm thick or more than 10mm and should have a final joint width of approximately 3 - 10mm. Use tile spacers if desired to ensure even spacing.
5. Remove any surplus adhesive on face of the tile or between joints before it sets.

6. Adjustment of tiles should be carried out within 15 minutes of laying (at 23°C and 50% relative humidity).

NOTE: Fixing tiles with water absorption less than 6% (dense tiles) and for external applications replace the water content with DUNLOP PRIMER & ADDITIVE or DUNLOP PRIMER.

COVERAGE

The coverage below is for the 15kg of DUNLOP FLOORFIX. Coverage will vary depending on the condition of the surface being tiled and application technique. As a general guide, coverage will be 3.75m² using a 10mm notch trowel.

DRYING TIME

Full traffic should be possible after 24 hours (at 23°C and 50% relative humidity). Allow longer for dense tiles/substrates, humid climates and low temperatures.

GROUTING

Wait until the adhesive has set firmly. This takes approximately 24 hours. Remove tile spacers and use DUNLOP GROUT adding DUNLOP PRIMER AND ADDITIVE to enhance colour, impart a degree of flexibility and reduce porosity and staining.

MOVEMENT JOINTS

Movement joints must be in accordance with AS 3958.1:2007. As a general guide, movement joints should be incorporated at 4.5 metre intervals and around the perimeter of the floor. These joints must be approximately 6mm wide and kept free from adhesive and grout. Any structural movement joints must be carried through to the face of the tiling. They should be filled with a suitable flexible material such as DUNLOP COLOURED SILICONE.

SHELF LIFE

A shelf life of 12 months is expected when stored in a dry place in original unopened container at 30°C and 50% relative humidity. Always re-seal bag air tight after use.

PACKAGING

15kg



FLOORFIX TILE ADHESIVE

CAUTION

Do not use in continuous immersed conditions such as swimming pools. Do not use over timber floors. Do not use DUNLOP FLOORFIX over concrete slabs subject to shrinkage and other movement. Use in conjunction with DUNLOP PRIMER AND ADDITIVE in exposed outdoor situations by replacing all of the water in the mixing process.

DUNLOP GUARANTEE

Product is guaranteed for 10 years when installed to manufacturers instructions. Manufactured under a quality system certified as complying with ISO 9001 by an accredited certification body.

TECHNICAL DETAILS

1. Characteristics of product:

Colour and Form: Grey powder
Bulk Density: 1.6kg / Litre

Application Properties (at 23°C and 50% relative humidity)

Mixing Ratio: 100:23 (powder: water)
Open Time: approx 15 minutes
Adjustability time: approx 25 minutes
Sagging: None
Pot Life: 2 hours

Mechanical Properties:	AS4992.1	Meets
Shear Bond Strength (Mpa):		
7 days dry	>1.0	Yes
14 days dry	>1.5	Yes
28 days dry:	-	
7 days water immersion:	>1.0	Yes
Tensile Strength (Mpa)		
7 days dry:	>0.15	Yes

SAFETY

Keep out of reach of children. Use gloves to prevent skin irritation. Avoid inhaling dust by using a dust mask. Wash immediately with plenty of water if material enters the eyes. Material Safety Data Sheet (MSDS) available on DUNLOP website.

USER NOTES

The technical details and recommendations contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is the responsibility of the user to ensure that the products are used in accordance with DUNLOP product instructions and in applications for which they are intended.

Exceeds Australian Standard AS 4992.1

ARDEX AUSTRALIA PTY LTD. ABN 82 000 550 00520
Powers Road, Seven Hills NSW 2147 Australia

ARDEX Australia Pty Ltd

NSW Ph (02)9851 9199 Fax (02)9838 7970
VIC Ph (03)8339 3100 Fax (03)9308 9332
QLD Ph (07)3817 6000 Fax (03)3881 3188
SA Ph (08)8406 2500 Fax (08)8345 3207
WA Ph (08)9256 8600 Fax (08)9455 1227

ARDEX New Zealand Ltd

Auckland Ph (09)580 0005 Fax (09)579 9963
Wellington Ph (04)568 5949 Fax (04)568 6376
Christchurch Ph (03)373 6900 Fax (03)384 9779

FFTA - 08/11